

INDUSTRIAL SANDS LTD. - sieve analysis.

SAND Concrete Sand

DATE: 3/12/2014

SAMPLE WEIGHT : 200

P4000

SIEVE	WGT RET.	% RET.	ACC. % RET.	% PASSING
3.150	0.40	0.20%	0.20%	99.80%
2.400	0.28	0.14%	0.34%	99.66%
2.000	0.12	0.06%	0.40%	99.60%
1.700	0.48	0.24%	0.64%	99.36%
1.000	11.14	5.57%	6.21%	93.79%
0.500	82.80	41.40%	47.61%	52.39%
PAN	105.95	52.98%	100.59%	-0.59%
TOTAL	201.17			

F.MOD: 0.08

