

INDUSTRIAL SANDS LTD. - sieve analysis.

SAND **Filtersand**

DATE: 18/03/2015

SAMPLE WEIGHT : **200**

SIEVE	WGT RET.	% RET.	ACC. % RET.	% PASSING
2.36	0.00	0.00%	0.00%	100.00%
1.18	35.28	17.64%	17.64%	82.36%
0.60	109.73	54.87%	72.51%	27.50%
0.300	46.79	23.40%	95.90%	4.10%
0.150	7.53	3.77%	99.67%	0.34%
PAN	0.77	0.39%	100.05%	-0.05%
TOTAL	200.10			

F.MOD: 2.86

