

INDUSTRIAL SANDS LTD. - sieve analysis.

SAND **Crushed Glass**

DATE : **20/11/2013**

SAMPLE WEIGHT : **200**

Filter media

SIEVE	WGT RET.	% RET.	ACC. % RET.	% PASSING
0.000	0.00	0.00%	0.00%	100.00%
0.000	0.00	0.00%	0.00%	100.00%
0.000	0.00	0.00%	0.00%	100.00%
2.000	1.21	0.61%	0.61%	99.40%
0.600	141.45	70.73%	71.33%	28.67%
pan	56.77	28.39%	99.72%	0.29%
TOTAL	199.43			

F.MOD: 0.72

