

INDUSTRIAL SANDS LTD. - sieve analysis.

SAND **Morta**

DATE : **8/12/2009**

SAMPLE WEIGHT : **200**

SIEVE	WGT RET.	% RET.	ACC. % RET.	% PASSING
2.360	0.00	0.00%	0.00%	100.00%
1.180	8.48	4.24%	4.24%	95.76%
0.600	78.65	39.33%	43.57%	56.44%
0.300	84.62	42.31%	85.88%	14.13%
0.150	25.86	12.93%	98.81%	1.19%
Pan	2.37	1.19%	99.99%	0.01%
TOTAL	199.98			

F.MOD: 2.32

